

# JS Wall Crete

## Single Component Cement Resurfacer

LOT#

### PRODUCT DESCRIPTION

JS Wall Crete is single component, cement based topping designed to smooth, resurface and repair concrete or masonry surfaces. Formulated with a fine aggregate system and bonding agent, JS Wall Crete is ideal for tilt-up panels. This coating material may be applied by trowel, brush, sponge-float or gloved hand.

### GENERAL USES

- Horizontal, vertical, and overhead concrete and masonry surfaces
- Filling in and resurfacing small cracks, voids and pits
- New and old surfaces

### INSTRUCTIONS FOR USE

#### *Surface Preparation*

Clean surface of all form coatings, dirt, oil, paint, or any other foreign material. Remove loose concrete. Prior to application, moisten surface with clean water for 15 minutes. Do not leave standing water.

#### *Mixing*

Mix JS Wall Crete with clean water at approximately 1.0 to 1.25 gallons of water per 40 lb. Mix for 3 minutes, and then let mixture stand for 3 – 5 minutes.

#### *Application*

Apply to surface with heavy brush, trowel, sponge float or gloved hand. When applying into cracks, voids, or pits, maximum thickness per application is 1/8" (.3 cm). Work mixture into surface with a trowel or sponge float. If a second coat is necessary, apply second coat before initial coat has cured. Initial set occurs 30-45 minutes after mixing, final set occurs 1.5 – 2.0 hours after mixing.

#### *Cleaning*

Water clean-up prior to cure.

### LIMITATIONS/WARNING

- Not to be used at temperatures below 40°F.
- Curing time will be slower in colder weather and faster in warmer weather.
- Not designed as a wearing surface.
- Do not over water.
- Use only potable water for mixing.

Refer to Material Safety Data Sheet prior to use.

Avoid direct contact with skin and eyes. Product contains Portland Cement. May cause irritation and possibly cement burns. Wash exposed skin area promptly with water. In case of eye contact, flood eyes repeatedly with water and call physician. Do not take internally. Harmful if ingested.

### KEEP PRODUCT OUT OF REACH OF CHILDREN

### TECHNICAL SERVICES

Jobsite Supply Technical Service Department provides complete product and technical support.

### PACKAGING

- 40 lb bags
- 40 lb pails



HIMS  
Hazard Ratings

- 0 - Least
- 1 - Slight
- 2 - Moderate
- 3 - High
- 4 - Extreme