



**SCOFIELD®
SYSTEMS**

www.scofield.com

CHROMIX® Admixtures for Color-Conditioned® Concrete

PRODUCT DESCRIPTIONS:

CHROMIX® Admixtures For Color-Conditioned® Concrete

Add strength and beauty to both vertical and horizontal construction projects with CHROMIX Admixtures. The reliable, nonfading and consistent coloring admixtures for cast-in-place and precast concrete have been proven to stand the test of time.

Available in three convenient forms:

- **CHROMIX P** (powdered)
- **CHROMIX ML** (mixed liquid) in buckets and totes
- **CHROMIX L** (liquid) available through selected ready-mix suppliers

The most popular colors are shown on this color chart. More than 400 color formulations are readily available, in addition to our custom matching service.

Beauty, Durability and Value

CHROMIX Admixtures provide streak-free color-conditioning and performance characteristics superior to concrete colored with raw pigments.

LITHOCHROME® Colorwax™ and COLORCURE® Concrete Sealer are available in matching colors.

SCOFIELD® Texturetop® is also available in colors to approximate those shown.

Review Tech-Data Bulletins and MSDS before use.

Visit www.scofield.com for the most current versions.



C-31 Shadow Slate*



5238 Sunbaked Clay



C-22 Coral Red



C-26 Antique Cork



3987 Porcelain Gray*



6063 Winter Beige



C-32 Quarry Red



5234 Summer Beige



1266 Cool Gray



0288 Autumn Beige



5059 Sorrento Red




5130 Spring Beige



C-14 French Gray



C-20 Limestone



C-27 Westwood Brown



C-15 Coachella Sand



C-24 Charcoal



C-25 Sombrero Buff



1017 Barcelona Brown



C-11 Desert Sand



C-34 Dark Gray



C-12 Mesa Beige



1010 Brownstone




C-21 Adobe Tan

* Porcelain Gray and Shadow Slate are only available in CHROMIX P (powdered) form.

Colors shown approximate the color of broom-finished concrete flatwork made with a medium-gray cement and cured with LITHOCHROME Colorwax or COLORCURE Concrete Sealer in the matching color. Concrete not so cured will have less brilliance.

Concrete should be batched and placed in accordance with Tech-Data Bulletins.

Concrete color is altered by many factors, including cement and aggregate color, slump, finishing practices, and curing method. Using the contemplated materials and construction techniques, representative samples should be cast for approval, especially when exact color matching is important.

© L. M. Scofield Company 2009 – All rights reserved. CHROMIX, COLORCURE, LITHOCHROME, SCOFIELD,  Color-Conditioned, Colorwax, and Texturetop are trademarks of L. M. Scofield Company.